

PEUGEOT
EV BATTERY ELECTROCHEMICAL PERFORMANCE AND DURABILITY INFORMATION

09.08.2024

Brand	Carline Family	Code	EV Type	Battery Model	Weight	Manufacturer	Place	Chemistry	Status	Rated capacity	Applied charge C-rate	Applied discharge C-rate	Power at max charge level	Power capability at 80% of the charge level (In kW)	Power capability at 50% of the charge level (In kW)	Power capability at 20% of the charge level (In kW)	Internal Resistance	Energy round trip efficiency	Ratio between nominal battery power (W) and battery energy (Wh)	Expected Lifetime (In number of equivalent reference cycle)	Expected lifetime (In calendar ageing)	Reference cycle used for expected lifetime
PEUGEOT	2008	P24	BEV	BS2-049-4-5	350 kg	Stellantis Auto SAS	Vigo, Spain ;	Li-Ion NMC	New	121 Ah	C/3 until 4.2 V then C/20	C/3 until 2.8V	196300 W	189.4 kW	174.5 kW	162.6 kW	0.1385 Ω	96 %	4.11 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	2008	P24	BEV	BS2-054-4-3_0	340 kg	Stellantis Auto SAS	Vigo, Spain ;	Li-Ion NMC	New	145.2 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	136000 W	136 kW	136 kW	135 kW	0.114 Ω	97 %	2.5 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	2008	P24	BEV	BS2-054-4-3_1	340 kg	Stellantis Auto SAS	Vigo, Spain ;	Li-Ion NMC	New	145.2 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	155000 W	155 kW	155 kW	155 kW	0.114 Ω	97 %	2.84 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	2008	P24	MHEV P2	BSX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	208	P21	BEV	BS2-049-4-4	350 kg	Stellantis Auto SAS	Zaragoza, Spain ;Poissy, France ;	Li-Ion NMC	New	121 Ah	C/3 until 4.2 V then C/20	C/3 until 2.8V	196300 W	189.4 kW	174.5 kW	162.6 kW	0.1385 Ω	96 %	4.12 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	208	P21	BEV	BS2-051-4-2	340 kg	Stellantis Auto SAS	Zaragoza, Spain ;	Li-Ion NMC	New	136 Ah	C/3 until 4.25V then C/20	C/3 until 2,5V	155000 W	155 kW	155 kW	155 kW	0.091 Ω	98.4 %	3.03 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	208	P21	MHEV P2	BSX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P84	PHEV	BM1-013-4-1	119 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.118 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P84	PHEV	BM1-014-4-1	135 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	131900 W	124.1 kW	115 kW	105.9 kW	0.131 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P64	PHEV	BM2-021-4-1	161 kg	Stellantis Auto SAS	Melfi, Italy ;Eisenach, Germany ;Rennes, France ;Sochaux, France ;	Li-Ion NMC	New	60 Ah	1C until 4.25V then C/20	1C up tp 2.8V	115000 W	115 kW	115 kW	115 kW	0.137 Ω	95.6 %	5.47 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P64	BEV	BM2-080-4-2	518 kg	Stellantis Auto SAS	Eisenach, Germany ;Melfi, Italy ;Sochaux, France ;	Li-Ion NMC	New	226 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	314000 W	314 kW	314 kW	248 kW	0.064 Ω	96.2 %	3.9 h-1	750 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P64	BEV	BM2-087-4-2	507 kg	Stellantis Auto SAS	Eisenach, Germany ;	Li-Ion NMC	New	237.7 Ah	C/3 until 4.2V then C/40	C/3 until 2.3V	285200 W	278.8 kW	254.5 kW	229.8 kW	0.0755 Ω	96 %	3.4 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P64	BEV	BM2-100-4-2	562 kg	Stellantis Auto SAS	Rennes, France ;Eisenach, Germany ;Melfi, Italy ;Sochaux, France ;	Li-Ion NMC	New	280 Ah	C/3 until 4.2V then C/40	C/3 until 2.3V	331800 W	325.4 kW	296.1 kW	268.7 kW	0.0646 Ω	96 %	3.36 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P64	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	3008	P84	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308	P51	PHEV	BM1-013-4-2	120 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.116 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308	P51	PHEV	BM1-017-4-1	139 kg	SVOLT	Changzhou City, P.R. China ;	Li-Ion NMC	Original	62.5 Ah	1C charge to 4.2V then switch to C/20 charge to 4.2V	1C discharge to 2.8V	137200 W	133.0 kW	108.7 kW	72.2 kW	0.075 Ω	97 %	8.3 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308	P51	BEV	BM1-054-4-2	340 kg	Stellantis Auto SAS	Russelsheim, Germany ;	Li-Ion NMC	New	145.2 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	155000 W	155 kW	155 kW	155 kW	0.114 Ω	97 %	2.84 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308	P51	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308 SW	P52	PHEV	BM1-013-4-2	120 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.116 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308 SW	P52	PHEV	BM1-017-4-1	139 kg	SVOLT	Changzhou City, P.R. China ;	Li-Ion NMC	Original	62.5 Ah	1C charge to 4.2V then switch to C/20 charge to 4.2V	1C discharge to 2.8V	137200 W	133.0 kW	108.7 kW	72.2 kW	0.075 Ω	97 %	8.3 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308 SW	P52	BEV	BM1-054-4-3	340 kg	Stellantis Auto SAS	Russelsheim, Germany ;	Li-Ion NMC	New	144 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	155000 W	155 kW	155 kW	155 kW	0.114 Ω	97 %	2.84 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	308 SW	P52	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	408	P54	PHEV	BM1-013-4-2	120 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.116 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	408	P54	PHEV	BM1-017-4-1	139 kg	SVOLT	Changzhou City, P.R. China ;	Li-Ion NMC	Original	62.5 Ah	1C charge to 4.2V then switch to C/20 charge to 4.2V	1C discharge to 2.8V	137200 W	133.0 kW	108.7 kW	72.2 kW	0.075 Ω	97 %	8.3 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	408	P54	BEV	BM1-062-4-2	365 kg	Stellantis Auto SAS	Russelsheim, Germany ;	Li-Ion NMC	New	155.8 Ah	C/3 until 4.25V then C/20	C/3 until 2,8V	204900 W	204.9 kW	204.9 kW	204.9 kW	0.099 Ω	96.86 %	3.32 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	408	P54	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)

PEUGEOT
EV BATTERY ELECTROCHEMICAL PERFORMANCE AND DURABILITY INFORMATION

09.08.2024

Brand	Carline Family	Code	EV Type	Battery Model	Weight	Manufacturer	Place	Chemistry	Status	Rated capacity	Applied charge C-rate	Applied discharge C-rate	Power at max charge level	Power capability at 80% of the charge level (In kW)	Power capability at 50% of the charge level (In kW)	Power capability at 20% of the charge level (In kW)	Internal Resistance	Energy round trip efficiency	Ratio between nominal battery power (W) and battery energy (Wh)	Expected Lifetime (In number of equivalent reference cycle)	Expected lifetime (In calendar ageing)	Reference cycle used for expected lifetime
PEUGEOT	5008	P74	PHEV	BM2-021-4-1	161 kg	Stellantis Auto SAS	Melfi, Italy ;Eisenach, Germany ;Rennes, France ;Sochaux, France ;	Li-Ion NMC	New	60 Ah	1C until 4.25V then C/20	1C up tp 2.8V	115000 W	115 kW	115 kW	115 kW	0.137 Ω	95.6 %	5.47 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	5008	P74	BEV	BM2-080-4-2	518 kg	Stellantis Auto SAS	Eisenach, Germany ;Melfi, Italy ;Sochaux, France ;	Li-Ion NMC	New	226 Ah	C/3 until 4.25V then C/20	C/3 until 2.5V	314000 W	314 kW	314 kW	248 kW	0.064 Ω	96.2 %	3.9 h-1	750 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	5008	P74	BEV	BM2-087-4-2	507 kg	Stellantis Auto SAS	Eisenach, Germany ;	Li-Ion NMC	New	237.7 Ah	C/3 until 4.2V then C/40	C/3 until 2.3V	285200 W	278.8 kW	254.5 kW	229.8 kW	0.0755 Ω	96 %	3.4 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	5008	P74	BEV	BM2-100-4-2	562 kg	Stellantis Auto SAS	Rennes, France ;Eisenach, Germany ;Melfi, Italy ;Sochaux, France ;	Li-Ion NMC	New	280 Ah	C/3 until 4.2V then C/40	C/3 until 2.3V	331800 W	325.4 kW	296.1 kW	268.7 kW	0.0646 Ω	96 %	3.36 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	5008	P74	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	5008	P87	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	508	R83	PHEV	BM1-013-4-1	119 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.118 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	508 SW	R82	PHEV	BM1-013-4-1	119 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.118 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Boxer	X250 Van	FCEV	BC3-013-4-1	119 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.116 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Boxer	X250 Van	BEV	BC3-110-4-2	655 kg	Stellantis Auto SAS	Gliwice, Poland ;	Li-Ion NMC	New	334 Ah	C/3 until 4.2V then C/20	C/3 until 2.8V	300000 W	298 kW	274 kW	255 kW	0.15 Ω	96 %	2.72 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Expert	K0 Van	FCEV	BC2-013-4-1	119 kg	LG Energy Solution	Wroclaw, Poland ;	Li-Ion NMC	New	40.8 Ah	1C until 4.2V then CV until C/20	1C until 2.5V	115400 W	108.6 kW	100.6 kW	92.7 kW	0.116 Ω	94.7 %	9.28 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Expert	K0 Van	BEV	BC2-049-4-2	350 kg	Stellantis Auto SAS	Hordain, France ;	Li-Ion NMC	New	145.8 Ah	C/3 until 4.25 V then C/20	C/3 until 2,5V	137400 W	137.4 kW	137.4 kW	137.4 kW	0.1023 Ω	97 %	2.86 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Expert	K0 Van	BEV	BC2-074-4-2	534 kg	Stellantis Auto SAS	Hordain, France ;	Li-Ion NMC	New	181.5 Ah	C/3 until 4.2 V then C/20	C/3 until 2,8V	243000 W	233 kW	219 kW	188 kW	0.062 Ω	97 %	3.26 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Expert Combi / Traveller	K0 Combi	BEV	BC2-049-4-2	350 kg	Stellantis Auto SAS	Hordain, France ;	Li-Ion NMC	New	145.8 Ah	C/3 until 4.25 V then C/20	C/3 until 2,5V	137400 W	137.4 kW	137.4 kW	137.4 kW	0.1023 Ω	97 %	2.86 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Expert Combi / Traveller	K0 Combi	BEV	BC2-074-4-2	534 kg	Stellantis Auto SAS	Hordain, France ;	Li-Ion NMC	New	181.5 Ah	C/3 until 4.2 V then C/20	C/3 until 2,8V	243000 W	233 kW	219 kW	188 kW	0.062 Ω	97 %	3.26 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Partner Van	K9 Van	BEV	BC1-052-4-1	380 kg	Stellantis Auto SAS	Ellesmere Port, United Kingdom ;Vigo, Spain ;	Li-Ion LFP	New	146.8 Ah	C/3 up to 3.8V then C/20	C/3 up to 2V	155000 W	155 kW	155 kW	155 kW	0.09057 Ω	95.4 %	2.98 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Partner Van	K9 Van	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Rifter Combi	K9 Combi	BEV	BC1-052-4-1	380 kg	Stellantis Auto SAS	Ellesmere Port, United Kingdom ;Vigo, Spain ;	Li-Ion LFP	New	146.8 Ah	C/3 up to 3.8V then C/20	C/3 up to 2V	155000 W	155 kW	155 kW	155 kW	0.09057 Ω	95.4 %	2.98 h-1	1000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)
PEUGEOT	Rifter Combi	K9 Combi	MHEV P2	BMX-001-0-1	12.2 kg	FinDreams Battery	Huizhou, P.R. China ;Chuzhou, P.R. China ;	Li-Ion NMC	New	20 Ah	1C up to 42V	1C down to 28V	28400 W	25.7 kW	22.6 kW	12.2 kW	0.007 Ω	98 %	27 h-1	22000 reference cycles	15 years	Specific cycling procedure dependent on the battery chemistry and the EV application (please contact us for more details)